

Appl. No. 10/716,392  
Amdt. Dated June 13, 2006  
Response to Office action of April 7, 2006

Listing of Claims

Please amend the claims as shown below. This listing of claims will replace all prior versions of claims and listings of claims in the application:

Claims 1-41. (canceled.)

42. (previously presented) A composite-coated structural wood construction product comprising:

a lumber substrate;

an intermediate composite layer coating a surface of the substrate; and

an outer composite layer coating the intermediate composite layer,

wherein each of the outer and intermediate composite layers includes a polymer and an organic filler,

wherein the organic filler is at least one of saw dust, wood flour, wood fibers, by-products of paper manufacturing, and recycled cellulose,

wherein a combination of all organic fillers is substantially between 20% and 80% by weight of the outer composite layer, and

wherein at least one of the intermediate layer and outer layers is foamed,

wherein the outer composite layer has an exterior surface substantially the same as an exterior surface of a non-structural plastic composite, and

wherein the intermediate and outer layers are extruded.

**BEST AVAILABLE COPY**

Appl. No. 10/716,392  
Amdt. Dated June 13, 2006  
Response to Office action of April 7, 2006

Claims 43-44. (canceled)

45. (previously presented) A composite-coated structural wood construction product according to claim 42, wherein the combination of all organic fillers is substantially between 30% and 60% by weight of the outer composite layer.

46. (previously presented) A composite-coated structural wood construction product according to claim 42, wherein the foamed composite layer has substantially between 5% and 80% less weight than an unfoamed composite layer with substantially the same volume as the foamed composite layer.

47. (previously presented) A composite-coated structural wood construction product according to claim 42, wherein the foamed composite layer has substantially between 10% and 50% less weight than an unfoamed composite layer with substantially the same volume as the foamed composite layer.

48. (previously presented) A composite-coated structural wood construction product according to claim 42, wherein the outer composite layer further includes a biocide.

Appl. No. 10/716,392  
Amdt. Dated June 13, 2006  
Response to Office action of April 7, 2006

49. (previously presented) A composite-coated structural wood construction product according to claim 42, wherein the substrate includes one of solid wood, compressed wood, and particle board.

50. (previously presented) A composite-coated structural wood construction product according to claim 42, wherein the substrate is treated with a protecting agent.

Claims 51-52. (canceled)

53. (new) A method of making a composite-coated structural wood construction product, the method comprising:

providing a lumber substrate;

extruding a foamed intermediate composite layer on a surface of the substrate; and

extruding an outer composite layer on the intermediate composite layer, so as to provide the outer composite layer with an exterior surface substantially the same as an exterior surface of a non-structural plastic composite,

wherein each of the outer and intermediate composite layers includes a polymer and an organic filler, wherein the organic filler is at least one of saw dust, wood flour, wood fibers, by-products of paper manufacturing, and recycled

Appl. No. 10/716,392  
Amdt. Dated June 13, 2006  
Response to Office action of April 7, 2006

cellulosics, and wherein a combination of all organic fillers is substantially between 20% and 80% by weight of the outer composite layer.

54. (new) A method according to claim 53, wherein the combination of all organic fillers provided in the outer composite layer is between 30% and 60% by weight.

55. (new) A method according to claim 53, wherein the foamed composite layer is provided with substantially between 5% and 80% less weight than an unfoamed composite layer with substantially the same volume as the foamed composite layer.

56. (new) A method according to claim 53, wherein the foamed composite layer is provided with substantially between 10% and 50% less weight than an unfoamed composite layer with substantially the same volume as the foamed composite layer.

57. (new) A method according to claim 53, wherein the outer composite layer is provided with a biocide.

58. (new) A method according to claim 53, wherein the substrate provided includes one of solid wood, compressed wood, and particle board.

Appl. No. 10/716,392  
Amdt. Dated June 13, 2006  
Response to Office action of April 7, 2006

59. (new) A method according to claim 53, wherein the substrate is treated with a protecting agent.

60. (new) A composite-coated structural wood construction product comprising:

a lumber substrate;

an intermediate layer providing a tight, form-fitting coat over the lumber substrate; and

an outer layer coating the intermediate layer,

wherein one of the outer and intermediate layers is a composite including a polymer and an organic filler,

wherein the organic filler is at least one of saw dust, wood flour, wood fibers, by-products of paper manufacturing, and recycled cellulose,

wherein a combination of all organic fillers is substantially between 20% and 80% by weight of the composite layer,

wherein the intermediate layer is foamed, and

wherein the intermediate and outer layers are extruded.

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**